

Series	Type	Product Code	Visible Light*		UV	Total Solar Energy*			Shading* Coefficient	IR Rejection (%)	Total Solar Energy Rejected (%)
			Transmitted (%)	Reflected (%)	Transmitted*	Transmitted (%)	Reflected (%)	Absorbed (%)			
Premium IR	C90	HCD-03G	5	4	<1	5	4	91	0.41	97	64
		HCD-10G	11	5	<1	9	5	86	0.44	95	61
		HCD-20G	22	5	<1	14	4	82	0.47	95	58
		HCD-30G	34	6	<1	18	5	77	0.50	95	56
		HCD-45G	50	6	<1	21	5	74	0.52	96	54
		HCN-60G	65	7	<1	31	5	64	0.60	95	47
		HCN-70	75	7	<1	36	5	59	0.64	94	44
Standard IR	C70	HCD-03G C70	7	4	<1	16	5	79	0.49	79	57
		HCD-10G C70	13	4	<1	21	5	74	0.52	76	54
		HCD-20G C70	26	5	<1	25	5	70	0.56	79	51
		HCD-30G C70	41	5	<1	32	5	63	0.60	79	47
		HCD-45G C70	54	6	<1	38	5	57	0.65	79	43
		HCN-60G C70	75	7	<1	45	6	49	0.70	80	38
		HCN-70 C70	81	8	<1	50	7	43	0.74	77	35
	C50	HCD-03G C50	7	4	<1	26	5	69	0.56	58	51
		HCD-10G C50	14	4	<1	30	5	65	0.59	59	48
		HCD-20G C50	29	5	<1	35	6	59	0.63	61	45
		HCD-30G C50	43	5	<1	44	6	50	0.69	58	39
		HCD-45G C50	56	6	<1	48	7	45	0.72	60	37
		HCN-60G C50	82	8	<1	60	6	34	0.81	59	29
		HCN-70 C50	85	8	<1	61	7	32	0.82	59	28
Safety IR	C90	HCD-45G Safety	39	6	<1	20	5	75	0.52	97	54
		HCN-60G Safety	60	7	<1	30	5	65	0.59	96	48
		HCN-70 Safety	71	7	<1	35	6	59	0.63	95	45
	C50	HCD-45G C50 Safety	56	6	<1	48	7	45	0.72	62	36
		HCN-60G C50 Safety	81	8	<1	58	7	35	0.79	63	30
		HCN-70 C50 Safety	85	8	<1	62	7	31	0.82	59	28
Clear IR	C70	IR-90HD	89	8	<1	71	8	21	0.89	69	22
3mm float glass			91	7	65	85	8	7	1.00	13	11

*In accordance with JIS S 3107:2013, "Adhesive film for automotive windows"

·IR rejection (%) is calculated by obtaining the average of solar energy transmittance at 780-2500nm and subtracting it from 100%.

·Total solar energy rejection (%) represents the proportion of solar radiation (heat) that does not pass through a glass unit with respect to the solar radiation incident to the glass.

The value is calculated by 100 - solar heat gain coefficient, which is shading coefficient x 0.88 x 100, based on JIS R 3106.